A Review of Thermal Insulation Bricks from Kaolin and Aluminum Oxide for Sustainable Construction

Aruna Devi[1], Dhirendra Pratap Singh[2], Rohit Srivastava[3]
[1]*M.Tech Scholar, Department of Production Engineering, S R Institute of Management & Technology (AKTU), Lucknow, India*
[2,3]*Assistant Professor,Department of Mechanical Engineering, S R Institute of Management & Technology (AKTU), Lucknow, India*
Mail id : arunadevi8948@gmail.com

Abstract—Recent advancements in eco-friendly building materials have highlighted kaolin-Al_2O_3)composites for its thermally insulated bricks. Because of its low thermal conductivity (0.15–0.25 W/m·K), refractory characteristics, and natural obtainability, kaolin is ideal for producing eco-friendly bricks[1]. Because of improved particle bonding, kaolin bricks with 10–30% Al_2O_3)reinforcement have a 30–50% increase in compressive strength. Nevertheless, high levels of Al_2O_3 (>30%) decrease workability and increase sintering costs [2]. Sawdust and other organic additives can add 30–50% porosity, which lowers thermal conductivity to 0.18–0.30 W/m·K. However, when porosity surpasses 50%, mechanical strength below 5 MPa may be compromised[3] . Inorganic additives such as perlite and vermiculite provide even better insulation (0.05–0.10 W/m·K), but their production costs increase by 20–25%. Energy comparisons have indicated that kaolin-AlO3 bricks have 30–50% less embodied energy and support superior thermal insulation performance when compared with burnt clay bricks.[4]. Not with standing these benefits, significant obstacles still exist, such as durability and increased expenses, necessitating more study into hybrid composites and nano-Al_2O_3 integration [5].

Keywords: Kaolin, Aluminum oxide (Al_2O_3), Thermal insulation bricks, Sustainable construction, Porosity, Hybrid composites, Nano-Al_2O_3.

1. INTRODUCTION

There has been a paradigm shift in the construction sector in recent years toward environmental responsibility, energy efficiency, and sustainability[6]. Despite their historical significance, traditional building materials like burned clay bricks are now important contributors to environmental degradation and energy use. High-temperature kilns used in the production of these bricks use fossil fuels and emit a lot of greenhouse gases, which contributes to resource depletion and global warming. Thus, the need for environmentally friendly, thermally efficient, and sustainable alternatives is greater than ever[6].

Kaolin-based composites have drawn interest among other options because of its special blend of affordability, natural availability, and encouraging mechanical and thermal qualities[7]. The clay mineral kaolin, which is mostly made up of kaolinite, is found in large quantities in nature and has good refractory qualities[8]. It is especially well-suited for insulation applications in building materials due to its naturally low thermal conductivity, which ranges from 0.15 to 0.25 W/m·K[9]. Kaolin enhances the compressive strength and thermal performance of composites when mixed with aluminum oxide (Al_2O_3)[10]. Because of improved matrix densification and particle bonding, studies have indicated that adding 10–30% Al_2O_3)can improve mechanical characteristics by as much as 50% [11].

The commercialization and widespread use of kaolin-Al_2O_3)composites are hindered by a number of obstacles, despite these encouraging characteristics. These include lower workability, durability problems under different climatic conditions, and the high cost of Al_2O_3)at larger percentages. Furthermore, in addition to having good performance, sustainable building materials need to be affordable and simple to manufacture with readily available local resources and basic technology[12]. Achieving desired attributes for practical use requires optimizing additive materials, sintering temperatures, and composite ratios, according to research[13] .

Investigating materials that provide lower embodied energy, lower carbon footprints, and improved indoor thermal comfort is also urgently needed given the increased focus on green certifications and building energy requirements[14]. Kaolin-based composites have the ability to satisfy these requirements while advancing circular economy building practices, particularly when modified with industrial wastes or nano-reinforcements. In order to overcome present constraints and investigate the possibilities of kaolin-Al_2O_3)composites as a sustainable substitute for traditional bricks, more thorough research is necessary.

2. LITERATURE REVIEW

Kaolin-Al_2O_3 composites have been extensively researched because of their intriguing mechanical and thermal characteristics[15]. Kaolin has become a popular material for insulating bricks because of its good refractory qualities and low heat conductivity, which ranges from 0.15 to 0.25 W/m·K[16]. Because of improved particle bonding, kaolin composites' compressive strength increases by roughly 30% to 50% when alumina (Al_2O_3) is added in the 10% to 30% range. Nevertheless, adding more than 30% Al_2O_3)raises sintering costs and degrades the material's workability, which makes it less viable for real-world uses[17].

Several additives are added to these composites to boost insulation and regulate porosity in order to further improve performance. Commonly used organic additions, such sawdust, can increase the material's porosity by 30% to 50%[18]. The thermal conductivity drops to between 0.18 and 0.30 W/m·K as a result of the increasing porosity. The material can only be used in non-load-bearing constructions, though, because its mechanical strength falls below 5 MPa when porosity surpasses 50%[19] . However, with conductivity as low as 0.05 to 0.10 W/m·K, inorganic additions like perlite and vermiculite offer better thermal insulation. However, using these additions raises production costs by roughly 20% to 25% [20].

In comparison to traditional burnt clay bricks, kaolin-Al_2O_3)bricks result overall superior features, with more superior insulation properties[12]. They have 30% to 50% less embodied energy, and 40% to 60% less thermal conductivity. That said, they still have a compressive strength of 5-15 MPa, which is still less than the compressive strength found in traditional concrete blocks that range from 20-50 MPa.

So kaolin-Al_2O_3)bricks can only be used in lightweight or non-structural construction. Time and again, these bricks have demonstrated promising results in practice, such as eco-housing projects in Germany where they have been able to realize energy savings of up to 25%[7].

Even with these benefits, there are still a number of problems to be solved, including durability issues like moisture absorption and freeze-thaw resistance, and production costs that are still 10% to 15% higher than those of conventional materials. Future research should therefore concentrate on adding nano-Al_2O_3 (1–5 wt.%) to further increase strength, creating hybrid composites using industrial waste materials like fly ash and slag , and carrying out large-scale production trials to evaluate commercial viability[7], [9] .

3. OVERVIEW OF KAOLIN & ALUMINUM OXIDE

3.1. Kaolin

Kaolin is a naturally occurring clay mineral with the chemical formula $Al_2Si_2O_5(OH)_4$[21]. It possesses low thermal conductivity (between 0.15 and 0.25 W/m·K), which allows it to be distinguished for use in insulating applications, and when heated to temperatures between 550 and 700°C, it transforms to metakaolin and the level of reactivity greatly improves[22].

The particle size is small (usually between 0.1 and 50 µm) which allows for very easy moulding and mixing processes, and the surface area is moderate (10 to 30 m^2/g) which creates good bonding in composite materials[8].

3.2. Aluminum Oxide

Aluminum oxide, or corundum, can be found in the chemically stable α-phase and is often known for its extreme hardness. It has high thermal stability (even up to 2000°C) and retains structural integrity at high temperatures. The addition of Al_2O_3)greatly enhances the strength and heat resistance of composite materials. Al_2O_3 small grain size, from nano to micro, also helps to facilitate surface bonding and increases toughness[23].

3.3. Application

3.3.1.Industrial Applications

Kaolin is extensively used in a wide range of industrial sectors, such as cement, paints, paper, rubber, and ceramics, due to its numerous applications[8]. However, aluminum oxide (Al_2O_3) is utilized in cutting tools, abrasives, refractories, and electronic substrates due to its hardness and heat endurance [24].

3.3.2.Energy Production

Due to its low thermal conductivity, kaolin is used for thermal insulation in kilns and power plants in the energy generation sector. Aluminium oxide is used in cutting-edge energy systems such as battery separators, high temperature insulating materials, and fuel cells[25].

3.3.3.Usage in Thermal Insulation

The mechanical strength of kaolin and a few percent to 30% aluminum oxide composite bricks increases from 30 to 50% while also maintaining a low thermal conductivity of 0.18–0.30 W/m·K, making them ideal for insulating applications. These bricks can retain high strength at high temperatures and are capable of providing structural shell behavior[26].

3.3.4.Challenges in Thermal Insulation

Aluminum oxide concentrations greater than 30% increase sintering temperatures and costs. Sawdust and other organic additions help enhance porosity in the produced ceramics but any amount higher than 50% will affect the mechanical strength. Perlite and vermiculite are two examples of inorganic additions which also improve insulation performance but will also potentially increase overall cost by 20-25%. Also, ensuring long-term durability under cyclic heating is still very difficult.[27]

3.4. Proposed Hybrid Mixture

For insulation bricks, a makeup of 70-80% kaolin, 15-25% aluminum oxide, and 5% organic or inorganic additives is ideal. This makeup gives bricks a durable and thermally efficient make-up that can be used in green construction. The nanoscale aluminum oxide adds to the strengthened particle and particle-to-

particles bonding potentials, even at lower concentrations[28].

3.5. Challenges and Future Developments

3.5.1.Challenges

The expensive cost of nano-scale aluminum oxide frequently prevents its adoption. Furthermore, more energy is required for the sintering process . The brittleness of bricks with a high aluminum oxide concentration restricts their use in structural applications [29].

3.5.2.Future Developments

In the future, nano-aluminum oxide will be included into composites to improve performance at lower content levels . Utilizing recovered industrial waste in conjunction with kaolin is another attractive strategy to reduce production costs.

In order to maximize the mechanical and infrared qualities of insulating materials, sophisticated AI-based design programs are currently under study. Additionally, 3D-printed brick production is becoming increasingly popular because it allows for personalized designs and minimizes material waste [30].

3.6. Market Overview: Cost and Availability

3.6.1.Cost Analysis

Kaolin is quite inexpensive, from $40 to $60 per ton.Aluminum oxide powder is relatively expensive; for micro-sized particles, it's from $800 to $1,200 per ton; and more than $2,000 per ton for nano-sized . Each insulating brick is estimated to cost from $0.45 to $0.70 to produce .4.6.2 Market Value

The insulation brick market is rapidly growing globally in response to the expanding use of energy efficient building materials. The market will grow at a compound annual growth rate (CAGR) of about 5.6% from 2023-2030, with demand primarily from the Asia, Europe and the Middle East.[31].

4. METHODLOGY

The present study explores the influence of kaolin and aluminum oxide (Al_2O_3) on the mechanical and thermal properties of burnt clay bricks by means of a review methodology of literature review. A wide range of reputable scientific databases including ScienceDirect, Elsevier, SpringerLink, and Google Scholar were searched for applicable peer-reviewed articles using specific keywords such as "kaolin thermal bricks," "Al_2O_3)reinforced clay bricks," "thermal conductivity of bricks," and "eco-friendly insulating materials."

Under this methodology, several processing methods, raw material ratios, and sintering temperatures found in the literature were evaluated critically. In particular, studies that partially replaced alumina as kaolin in amounts ranging from 10% to 30% is noteworthy[32]. The workability results from adding Al_2O_3)in the range show a consistent increase in compressive strength and thermal resistance, despite alumina's refractory properties, and in particular its effect on the densification of the microstructure. However, workability is inhibited as percentages of Al_2O_3)increase and bricks become more brittle[29].

The impacts of the additives for porosity and thermal insulation were assessed. It was found that organic additives, such as saw dust and rice husk ash, increased porosity and thus lower thermal conductivity, however at the expense of mechanical strength. In contrast, bricks are suitable for higher temperature applications where structural stability due to inorganic additions such as perlite and vermiculite aid in possible thermal insulation [28].

The key performance indicators presented for the evaluated research on ABS, including bulk density, compressive strength, thermal conductivity, and water absorption, were summarized in order to facilitate comparisons.

This systematic synthesis of literature provides a strong basis for sustainable kaolin-AI_2O_3 composite bricks, from which we can determine the optimal material compositions and processing parameters to provide a balanced performance in mechanical strength and thermal insulation[33].

5. RESULTS

It is clear from the structured literature syntheses that adding aluminum oxide (Al_2O_3) to kaolin-based clay matrices greatly improves their mechanical strength and thermal resistance. Because of the refractory nature of alumina and improved microstructural densification, a substitution ratio of 10–30% (Al_2O_3) reliably increases compressive strength by roughly 30–50% [33], [34].

Additionally, research indicates that adding organic elements like sawdust and rice husk ash can contribute 30 to 50% porosity, which can reduce thermal conductivity by up to 40% while also affecting structural strength[18]. By decreasing thermal conductivity while maintaining mechanical stability, inorganic additions like perlite and vermiculite, on the other hand, achieve a better balance, even though their production costs are higher [16].

6. CONCLUSION

Compared to conventional burnt clay bricks, kaolin-Al_2O_3)composites have improved thermal insulation, lower embodied energy and greater mechanical durability under mild thermal stress . All performance outcomes indicate the excellent performance of kaolin-Al_2O_3)composites as energy efficient and eco-friendly building products. This rigorously demonstrate the compatibility between aluminum oxide (Al_2O_3) and kaolin to develop eco-friendly thermal insulation bricks. Kaolin can thus serve a dual purpose, given its inherent low heat

conductivity, as a structural or insulation component when mixed with 10–30% Al_2O_3)requirement improved compressive strength and thermal performance. However, an increase in Al_2O_3)will result in a brittle material due to the increase in sintering energy requirements, and the brittleness increases when the optimum range is exceeded. While inorganic fillers have lower energy conductivity and improved rigidity, they also drive up production cost and energy consumption, while organic fillers can achieve greater porosity and lower thermal conductivity, but they generally compromise the mechanical properties.

7. FUTURE WORK

The results of this investigation present multiple pathways to enhance the functionality and performance of kaolin-Al_2O_3)composite bricks and future research should focus on the integration of nano-sized aluminum oxide (1-5%) to enhance compressive strength and microstructural densification without substantial negative ramifications to workability or added costs. In addition, kaolin or alumina may be substituted in part or completely by industrial wastes such as fly ash, slag, or red mud so as to lower production costs, decrease environmental impact, and contribute to sustainable building practices. The growing inclusion of artificial-intelligence and machine learning to optimize raw material ratios, sintering conditions, and performance outputs is another exciting area which may provide pathways to reduce the time lost on experimentations and materials consumption[31], [33].

Moreover, advanced manufacturing techniques such as 3D printing warrant further exploration in developing bricks with complex geometries, integrated insulating layers, and controlled porosity capable of meeting the high performance criteria for contemporary building. Additionally, for the full evaluation of practicality, sustained durability studies over time with exposure to various climate conditions - moisture, freeze-thaw cycles, chemical attacks, etc. - is required. Life cycle assessments (LCA) and techno-economic assessments will require as well to evaluate the market-readiness and scalability of these bricks[32], [34].

Lastly, hybrid systems that incorporate both organic and inorganic additives may help create bricks that will have adequate mechanical strength and thermal insulation properties for a variety of climate conditions and will enjoy widespread usage. The combined purpose of these future research endeavors is to overcome current limits and create kaolin-Al_2O_3)bricks[16], [17].

REFERENCES

[1] J. Kimani, "Thermal conductivity of refractory brick materials," 1989, Accessed: Jun. 03, 2025 https://erepository.uonbi.ac.ke/handle/11295/22288

[2] C. Keter, "Development and testing of composite refractory bricks (a case study of selected Kenyan clays)," 2016, Accessed: Jun. 03, 2025. [Online]. Available: https://www.academia.edu/download/104232268/Development_20and_20testing_20of_20composite_20refractory_20bricks.pdf

[3] U. Robert, S. Etuk, … O. A.-I. J. of, and undefined 2024, "Development of lightweight sawdust-based composite panels for building purposes," *Elsevier*, Accessed: Jun. 03, 2025. [Online]. Available: https://www.sciencedirect.com/science/article/pii/S2588840424000441

[4] L. Cabeza, A. Pisello, F. R.-H. of E. Efficiency, and undefined 2018, "Innovative and advanced insulation materials and systems," *books.google.com*, Accessed: Jun. 03, 2025.

[5] P. R. Rao, M. Momayez, K. A. Runge, and K. Muralidharan, "Recent developments in thermally insulating materials based on geopolymers—a review article," *Springer*, vol. 37, no. 4, pp. 995–1014, Aug. 2020, doi: 10.1007/S42461-020-00201-0.

[6] Y. H. Ahn, A. R. Pearce, and K. Ku, "Paradigm shift of green buildings in the construction industry," *Taylor & Francis*, vol. 2, no. 1, pp. 52–62, 2011, doi: 10.5390/SUSB.2011.2.1.052.

[7] H. R. Ahmad, Z. U. R. Farooqi, M. Sabir, and M. F. Sardar, "Brick Kilns: Types, Emissions, Environmental Impacts, and their Remedial Measures," *Springer*, vol. 2, pp. 945–958, Jan. 2022, doi: 10.1007/978-3-030-73943-0_52.

[8] W. J.-T. of the R. S. of and undefined 1984, "Kaolins: their properties and uses," *royalsocietypublishing.org*, no. A311, pp. 411–432, 1984, doi: 10.1098/RSTA.1984.0037.

[9] S. H. Hameed, "REDUCING BUILDING THERMAL LOADS BY ADDING WASTE TO CONSTRCTION MATERIALS," 2023, https://cnj.atu.edu.iq/wp-content/uploads/2024/05/Shahad-Hasan-final-30-12-23-3.pdf

[10] T. Ali, O. Zaid, and M. Z. Qureshi, "Impact of mechanical and thermal treatment of kaolin clay on the engineering properties of concrete," *Springer*, Feb. 2024, doi: 10.1007/S13369-024-09028-Z.

[11] I. Sabry, M. E.-D.-T. I. J. of Advanced, and undefined 2025, "Enhanced structural integrity and tribological performance of Al6061–Al6082 alloys reinforced with TiB2 and Al2O3 via friction stir welding," *Springer*, vol. 138, pp. 2893–2910, 2025, doi: 10.1007/S00170-025-15706-5.

[12] S. Rajendran, G. Palani, V. Shanmugam, H. T.- Molecules, and undefined 2023, "A Review of Synthesis and Applications of Al2O3 for Organic Dye Degradation/Adsorption," *mdpi.com*, Accessed: Jun. 03, 2025. [Online]. Available: https://www.mdpi.com/1420-3049/28/23/7922

[13] S. Yuan, F. Shen, C. Chua, K. Z.-P. in P. Science, and undefined 2019, "Polymeric composites for powder-based additive manufacturing: Materials and applications," *Elsevier*, Accessed: Jun. 03, 2025. [Online]. Available: https://www.sciencedirect.com/science/article/pii/S0079670018300261

[14] W. Ng, M. Chin, J. Zhou, K. Woon, A. C.- Energy, and undefined 2022, "The overlooked criteria in green building certification system: Embodied energy and thermal insulation on non-residential building with a case study in Malaysia," *Elsevier*, Accessed: Jun. 03, 2025. [Online]. Available: https://www.sciencedirect.com/science/article/pii/S036054422201814X

[15] E. Abdrakhimova, V. A.-I. materials: applied, and undefined 2018, "Formation of glaze coatings of clinker bricks based on raw kaolin and aluminum-containing nanotechnogenic raw materials," *Springer*, vol. 9, no. 4, pp. 588–594, Jul. 2018, doi: 10.1134/S2075113318040020.

[16] J. Kimani, "Thermal conductivity of refractory brick materials," 1989, Accessed: Jun. 03, 2025. https://erepository.uonbi.ac.ke/handle/11295/22288

[17] I. Ogunrinola *et al.*, "Silica and kaolin reinforced aluminum matrix composite for heat storage," *degruyter.com*, vol. 62, no. 1, Jan. 2023, doi: 10.1515/RAMS-2022-0305/HTML.

[18] S. Zou *et al.*, "Research on improving comprehensive properties of a new sawdust composite insulation material by torrefaction," *Elsevier*, Accessed: Jun. 03, 2025. [Online]. Available: https://www.sciencedirect.com/science/article/pii/S0957582021003050

[19] S. Zou *et al.*, "Experimental research on an innovative sawdust biomass-based insulation material for buildings," *Elsevier*, Accessed: Jun. 03, 2025 https://www.sciencedirect.com/science/article/pii/S0959652620310763

[20] S. Abidi, B. Nait-Ali, Y. Joliff, C. F.-C. P. B. Engineering, and undefined 2015, "Impact of perlite, vermiculite and cement on the thermal conductivity of a plaster composite material: Experimental and numerical approaches," *Elsevier*, Accessed: Jun. 03, 2025. https://www.sciencedirect.com/science/article/pii/S1359836814003102

[21] E. O.-J. of E. R. and and undefined 2025, "MINERALOGICAL CHARACTERIZATION OF ISUA CLAY FOR HIGH TEMPERATURE APPLICATIONS," *berkeleypublications.com*, vol. 27, no. 5, 2025, doi: 10.70382/bejerd.v7i5.005.

[22] "Improving insulation in metakaolin based geopolymer: Effects of metabauxite and metatalc," *Elsevier*, Accessed: https://www.sciencedirect.com/science/article/pii/S2352710218302973

[23] L. L.-S. C. of E. Materials and undefined 2019, https://www.sciencedirect.com/science/article/pii/B9780081020968000136

[24] A. A.-R. and I. Ceramics and undefined 2019, "Aluminum Oxide and Alumina Ceramics (review). Part 1. Properties of Al2O3 and Commercial Production of Dispersed Al2O3," *Springer*, vol. 60, no. 1, pp. 24–32, May 2019, doi: 10.1007/S11148-019-00304-2.

[25] O. Gohar, M. Khan, I. Bibi, N. Bashir, U. T.-M. & Design, and undefined 2024, "Nanomaterials for advanced energy applications: Recent advancements and future trends," *Elsevier*, Accessed: Jun. 03, 2025. [Online]. https://www.sciencedirect.com/science/article/pii/S0264127524003034

[26] I. Ogunrinola *et al.*, "Silica and kaolin reinforced aluminum matrix composite for heat storage," *degruyter.com*, vol. 62, no. 1, Jan. 2023, doi: 10.1515/RAMS-2022-0305/HTML.

[27] H. Gao *et al.*, "Improvement of durability of porous perlite geopolymer-based thermal insulation material under hot and humid environment," *Elsevier*, Accessed: Jun. 04, 2025. https://www.sciencedirect.com/science/article/pii/S0950061821031573

[28] U. U. org/10.3390/min13010091 and undefined 2023, "A review of particle shape effects on material properties for various engineering applications: from macro to nanoscale. Minerals 2023, 13, 91," *academia.edu*, vol. 13, no. 1, Jan. 2023, doi: 10.3390/MIN13010091,.

[29] A. Kr Singh, "Study on the effect of different sols on high alumina castable refractory," 2017, Accessed: Jun. 04, 2025. [Online]. Available: http://ethesis.nitrkl.ac.in/8643/

[30] I. Fidan, O. Huseynov, M. Ali, S. Alkunte, M. R.-Inventions, and undefined 2023, "Recent inventions in additive manufacturing: Holistic review," *mdpi.com*, Accessed: Jun. 04, 2025.https://www.mdpi.com/2411-5134/8/4/103

[31] S. Jonnala, D. Gogoi, S. Devi, M. K.-C. and building, and undefined 2024, "A comprehensive study of building materials and bricks for residential construction," *Elsevier*, Accessed: Jun. 04, 2025. https://www.sciencedirect.com/science/article/pii/S0950061824010729

[32] D. Tarek, M. Elnagar, H. Sameh, A. Yousef, and A. Ragab, "Energy Efficiency Coupled with Lightweight Bricks: Towards Sustainable Building: A review," *svusrc.journals.ekb.eg*, vol. 4, no. 1, pp. 1–28, 2023, doi: 10.21608/svusrc.2022.155971.1063.

[33] N. A. M. Barakat *et al.*, "Advanced strategies for enhancing kaolin ceramics using nanostructured additives: A comprehensive study," *journals.plos.org*, vol. 20, no. 5 May, May 2025, doi: 10.1371/JOURNAL.PONE.0324449.

[34] Y. Nasr, H. El Zakhem, A. Hamami, M. E. B.- Energies, and undefined 2023, "Comprehensive review of innovative materials for sustainable buildings' energy performance," *mdpi.com*, Accessed: Jun. 03, 2025. [Online]. Available: https://www.mdpi.com/1996-1073/16/21/7440